

külön kiadások, referenciák

KFKI-1987-49/E

A. G. BALOGH
L. LISZKAY
W. PUFF
B. MOLNÁR

POSITRON ANNIHILATION STUDY ON
Y-Ba-Cu-O HIGH T_c SUPERCONDUCTORS

Hungarian Academy of Sciences

**CENTRAL
RESEARCH
INSTITUTE FOR
PHYSICS**

BUDAPEST

POSITRON ANNIHILATION STUDY ON
Y-Ba-Cu-O HIGH T_c SUPERCONDUCTORS

A.G. BALOGH, L. LISZKAY, W. PUFF*, B. MOLNÁR

Central Research Institute for Physics
H-1525 Budapest 114, P.O.B. 49, Hungary

*Institut für Kernphysik
Technische Universität Graz
A-8010 Graz, Austria

Submitted to Phys. Rev. Lett.

A.G. Balogh, L. Liskay, W. Puff, B. Molnár: Positron annihilation study on Y-Ba-Cu-O high T_c superconductors. KFKI-1987-49/E

ABSTRACT

First positron annihilation measurements are reported on high T_c superconductor $YBa_2Cu_3O_{7-x}$. The lifetime and Doppler broadening spectra show a slight but significant change about 240K suggesting a deviation from the normal structure far above 90K where the resistance falls to zero. ✓

А.Г.Балог, Л.Лискай, В.Пуф, Б.Молнар: Исследование аннигиляции позитронов в высокотемпературном сверхпроводящем веществе Y-Ba-Cu-O. KFKI-1987-49/E

АННОТАЦИЯ

Впервые в литературе опубликовываются результаты исследования аннигиляции позитронов в высокотемпературном сверхпроводящем веществе $YBa_2Cu_3O_{7-x}$. Наблюдаемые при 240K малые, но значимые изменения спектров времени жизни и доплеровского расширения обосновывают предположения о том, что отклонения от нормальной структуры появляются намного выше температуры 90 K, при которой сопротивление падает до нуля.

Balogh A.G., Liskay L., Puff, W., Molnár B.: Pozitronannihilációs vizsgálatok magas hőmérsékletű Y-Ba-Cu-O szupravezetőn. KFKI-1987-49/E

KIVONAT

Pozitronannihilációs méréseket végeztünk - a szakirodalomban elsőként - magas hőmérsékletű $YBa_2Cu_3O_{7-x}$ szupravezető anyagon. Az élettartam és a Doppler spektrumok kismértékű, de szignifikáns változása 240 K környékén azt sugallja, hogy a szupravezető átmenet már jóval 90 K fölött, ahol az ellenállás értéke zérussá válik, megkezdődik.

First detailed positron annihilation measurements are reported on high T_c superconductor $YBa_2Cu_3O_{7-x}$. The lifetime and Doppler broadening spectra show a slight but significant change about 240 K suggesting a deviation from the normal structure far above 90 K where the resistance falls to zero.

The third generation of superconductors after some metals and alloys ($T_c^{\text{max}}(\text{Pb}) \approx 7.22$ K) and the A_3B intermetallic compounds [1,2] (where $A=\text{Nb}, \text{V}$; $B=\text{Si}, \text{Ge}, \text{Sn}, \text{Ga}$ and $T_c^{\text{max}}(\text{Nb}_3\text{Ge}) \approx 23.2$ K), shows a transition temperature of about 90 K exceeding the liquid nitrogen temperature and making the technical utilization of the superconductors more attractive.

The BCS theory [3], which was one of the best developed theory in the physics, is not perfectly adequate for the new oxide ceramics, where the mean distance of the Cooper pairs is shorter, the interaction between the two electrons is stronger than earlier. Therefore beside the phonon-electron interaction new terms are necessary to describe satisfactorily the high temperature superconductivity of these compounds. After the first publications [4-6] it seems to be clear that the Cu-O planes/chains take place at the superconductivity and so far the O-vacancies and/or the charge state of the Cu atoms play an important role. While the positron annihilation method has a unique sensitivity for vacancy-like defects and reflects properly the change of the electron density it seemed to be straightforward to perform some positron annihilation measurement to clear up the properties of this new superconductors about the transition temperature.

Samples were prepared* from Y_2O_3 , $BaCO_3$ and CuO by mixing and heating at 950°C for 2h in air. After pressing into pellets at 7.5 t/cm^2 their were reheated to 1000°C for 2h in oxygen flow for sintering and cooled down slowly during 3h.

*Samples were prepared by Drs. B. Molnar, L. Bottyan and Mr. F. Gazdaccka, Nucl. Phys. Dept., CRIP, Hungary

The temperature dependent resistivity measurements showed a transition temperature (T_c) of about 92 K [7]. The neutron diffraction measurements verified the orthorhombic structure, which is typical for superconducting materials in the case of $x > 6.5$ (mixed valence state) [8]. Cooling down to liquid nitrogen temperature the samples showed the Meissner effect holding a Co-Sm magnet of 45 mg in floating some 2 mm above the surface.

On a pair of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ samples positron lifetime and Doppler broadening measurements were performed between RT and 30 K. Lifetime spectra were measured with a spectrometer having a time resolution of 270 ps full width at half maximum. Each spectrum contained 6×10^6 counts accumulated over a 20h period. The positron source was rather strong, 35 μCi of $^{22}\text{NaCl}$, and was deposited on a 5 μm thick Al foil. The source correction was determined to consist of a 251 ps component with 6.6% intensity and a 450 ps component amounting to 2.0%. Numerical analysis was performed by the programme described in Ref. 9.

The solid state detector, applied for the Doppler broadening measurements, was a HP-Ge coaxial detector with an energy resolution of 1.18 keV at the 497 keV ^{103}Ru γ -line. The spectrometer was digitally stabilized (zero and gain) using ^7Be and ^{207}Bi , and spectra were accumulated to about 8×10^6 counts in the annihilation spectrum.

Lifetime and Doppler broadening measurements were repeated several times by cooling down and heating up the samples between RT and 80 K. The small change (1-2%) in the mean lifetime and in the S parameter of the Doppler broadening measurements is significant and reproducible at each time passing by the temperature of 240 K. (See Table 1.) Both parameters (τ , S) are higher at low temperature. The size of the superconducting crystallites is typically about 1 μm [10,15,16] which is however large enough to avoid the positrons to escape if they already thermalized there. The small change of the positron parameters indicates that the average electron density doesn't vary drastically at the transition.

The good quality two-component analysis ($\chi^2 \approx 1.01$ typically) show a detailed picture. (Table 2.) It is not surprising that there are two strongly different components because these polycrystalline compounds contain generally not only one phase.

We suggest that the drastical change in the first component (τ_1, I_1) correlates with the superconducting transition of the crystallites, while the second component arises from the other probably amorphous phase which separates the crystalline grains and comprises some 10% of the sample [15].

Although the oxygen deficiency of these kind of materials is rather small ($x \approx 0.1-0.5$ typically, depending on heat treatment [14]) it results an O-vacancy concentration of about $10^{-1}-10^{-2}$. If these vacancies would trap the positrons we ought to see a saturation (the probability of thermal detrapping at this temperature is negligible), however it is not the case. The Cu-O planes contain Cu^{3+} and Cu^{2+} atoms with an average valence, which is changing from 2.33 (at $x=7$) to 1.67 (at $x=6$), [11,17] meaning in our case a ratio of about 30% Cu^{3+} and 70% Cu^{2+} . Most of the O-vacancies are probably locally positive consequently they are not attractive for the positrons. If there would be some change in the $\text{Cu}^{3+}/\text{Cu}^{2+}$ ratio at the transition, it could be followed by a lattice relaxation and some of the positively charged O-vacancies could be filled up with electrons producing neutral or negatively charged O-vacancies which can trap the positrons. Although the coordination and the lattice structure are different it is stimulating that the 179 ps value of τ_1 at low temperature agrees very good with the vacancy lifetime in pure Cu [12].

There is some contradiction in the literature and especially in the private communications whether the transition temperature of about 240 K reported by more laboratories (see for example [13,16]), is reliable or not. Our results show a significant and reversible change in the positron parameters about 240 K. If this change correlates with the superconducting transition, as we believe it, it would indicate that this transition takes place in some crystallites already at about 240 K, however this effect will be macroscopic only about 90 K, where the resistance falls to zero. On the other hand some structural change in the superconducting crystallites as a reason of the higher lifetime can not be excluded.

We hope that these first detailed positron annihilation results will stimulate further measurements on the high T_c superconductors. Angular correlation measurements would be fruitful in

getting information about the distribution of electron density and the charge density at the Fermi level. Positron annihilation measurements depending on magnetic field could be check whether the expected change in T_c correlates with the jump in positron parameters.

ACKNOWLEDGMENTS

The authors are grateful to Drs. Gy. Hutiray and D.L. Nagy for fruitful discussions.

This work was partly supported by a grant for high T_c superconductors given by MTA KFKI.

REFERENCES

- [1] J.R. Gavaler: Appl. Phys. Lett. 23, 480 (1983)
- [2] G. Brauer, A. Balogh, A. Andreeff: Appl. Phys. 17, 421 (1978)
- [3] J. Bardeen, L.N. Cooper, J.R. Schrieffer: Phys. Rev. 106, 162 (1957)
- [4] J.G. Bednorz, K.A. Muller: Z. Phys. B 64, 189 (1986)
- [5] S. Massada, J.Yu, A.J. Freeman, D.D. Koelling: Phys. Lett. A 122, 198 (1987)
- [6] C.W. Chu, P.H. Hor, R.L. Meng, L. Gao, Z.J. Huang, Y.Q. Wang: Phys. Rev. Lett. 58, 408 (1987)
- [7] L. Bottyán et al., to be published
- [8] L. Mihály et al.: Submitted to Phys. Rev. Lett.
- [9] W. Puff: Comp. Phys. Comm. 30, 359 (1983)
- [10] E.A. Hewat, M. Dupui, A. Bourret, J.J. Capponi, M. Marenzio: Nature 327, 400 (1987)
- [11] W.I.F. David et al.: Nature 327, 311 (1987)
- [12] M.J. Fluss, C.C. Smedskjaer, R.W. Siegel, D.G. Legmini, M.K. Chason: J. Phys. F. 10, 763 (1980)
- [13] B. Jayaram, S.K. Agarwal, A. Gupta, A.V. Narlikar: Jap. J. of Appl. Phys. 26, 1004 (1987)

- [14] P. Strobel, J.J. Capponi, C. Chaillout, M. Marezio,
J.L. Tholence: Nature 327, 306 (1987)
- [15] A. Ourmazd, J.A. Reutschler, J.C.H. Spence, M.O'Keefee,
R.J. Graham, D.W. Johnson, Jr., W.W. Rhodes: Nature 327, 308
(1987)
- [16] J.T. Chen, L.E. Wenger, C.J. McEwan, E.M. Logothetis: Phys.
Rev. Lett. 58, 1972 (1987)
- [17] P.K. Gallagher, H.M. O'Brian, S.A. Sunshine, D.W. Murphy:
Mat. Res. Bull. to be published

Table 1. Temperature dependence of S and τ parameters

Temp. range (K)	S	τ (ps)
80 - 240	0.417 (± 0.001)	185.5 (± 1)
250 - RT	0.413 (± 0.001)	180.3 (± 1)

Table 2. Results of two-component analysis of lifetime spectra vs. temperature

	RT	250 K	240 K	80 K
τ_1 (ps)	146 (± 2)	143 (± 2)	176 (± 2)	179 (± 2)
τ_2 (ps)	218 (± 3)	218 (± 3)	243 (± 3)	243 (± 3)
I_1 (%)	50.86 (± 1.36)	43.04 (± 1.18)	77.17 (± 2.38)	89.62 (± 2.36)

The issues of the KFKI preprint/report series are classified as follows:

- | | |
|---|--|
| A. Particle and Nuclear Physics | H. Laboratory, Biomedical and Nuclear Reactor Electronics |
| B. General Relativity and Gravitation | I. Mechanical, Precision Mechanical and Nuclear Engineering |
| C. Cosmic Rays and Space Research | J. Analytical and Physical Chemistry |
| D. Fusion and Plasma Physics | K. Health Physics |
| E. Solid State Physics | L. Vibration Analysis, CAD, CAM |
| F. Semiconductor and Bubble Memory Physics and Technology | M. Hardware and Software Development, Computer Applications, Programming |
| G. Nuclear Reactor Physics and Technology | N. Computer Design, CAMAC, Computer Controlled Measurements |

The complete series or issues discussing one or more of the subjects can be ordered; institutions are kindly requested to contact the KFKI Library, individuals the authors.

Title and classification of the issues published this year:

- | | |
|---|--|
| KFKI-1987-01/A
V.Sh. Gogokhia et al. | Nonperturbative approach to quark propagator in the covariant, transverse gauge |
| KFKI-1987-02/M
M. Barbuceanu et al. | Integrating declarative knowledge programming styles and tools for building expert systems |
| KFKI-1987-03/G
L. Szabados et al. | Primary loop dynamical investigations. Part 1. Computerized analysis of the total loss of flow in the Paks NPP on the basis of PMK-NVH experimental data /in Hungarian/ |
| KFKI-1987-04/G
Gy. Egely | Critical comparison of nuclear safety reports. Part 1. Practice followed in the USA and in FRG /in Hungarian/ |
| KFKI-1987-05/G
Gy. Ézsöl et al. | A 7.4% cold leg break without SIPs. Description of the measurement /in Hungarian/ |
| KFKI-1987-06/G
Gy. Ézsöl et al. | Primary loop dynamical investigations. Part 1. Experimental investigation of the total loss of flow in the Paks NPP in the PMK-NVH facility /in Hungarian/ |
| KFKI-1987-07/G
L. Szabados et al. | A calculation method for the operation of the Paks NPP based on the subchannel approach. Part 1. A computing procedure and method applicable as part of the VERONA system /in Hungarian/ |
| KFKI-1987-08/B
L.B. Szabados | Commutation properties of cyclic and null Killing symmetries |
| KFKI-1987-09/E
G. Györgyi et al. | Relaxation processes in chaotic states of one dimensional maps |
| KFKI-1987-10/D
Gy. Egely | Hungarian ball lightning observations (case 1 - case 278) |

KFKI-1987-11/M H. König	Developing protocol test software using the PDL-system
KFKI-1987-12/M D. Nicholson et al.	Advanced help through plan instantiation and dynamic partner modelling
KFKI-1987-13/M Katalin Tarnay et al.	Experiments with a network environment manipulator /in Hungarian/
KFKI-1987-14/A H.W. Barz et al.	Deconfinement transition in anisotropic matter
KFKI-1987-15/M R. Wittmann	An algebraic specification method for describing the protocols of computer networks /in Hungarian/
KFKI-1987-16/G O. Aguilar et al.	Monitoring temperature reactivity coefficient by noise method in a NPP at full power
KFKI-1987-17/M G. Németh et al.	Collection of scientific papers in collaboration with Joint Institute for Nuclear Research, Dubna, USSR and Central Research Institute for Physics, Budapest, Hungary. Algorithms and programs for solution of some problems in physics. Fifth volume
KFKI-1987-18/E G. Egely et al.	Experimental investigation of biologically induced magnetic anomalies
KFKI-1987-19/A B. Milek et al.	A model for particle emission from a fissioning system
KFKI-1987-20/M S. Wagner-Dibuz	The specification and testing of transport protocols /in Hungarian/
KFKI-1987-21/E B. Lukács et al.	Elementary quantum physical description of triplet superconductors
KFKI-1987-22/G M. Makai et al.	DIGA/NSL - New calculational model in slab geometry
KFKI-1987-23/A J. Erő et al.	Production of protons, deuterons and tritons on carbon by intermediate energy neutrons
KFKI-1987-24/K I. Balásházy et. al	Gamma-spectrometric examination of hot particles emitted during the Chernobyl accident
KFKI-1987-25/K A. Andrászi et al.	Application of Ge-spectrometry for rapid in-situ determination of environmental radioactivity
KFKI-1987-26/G J. Végh	Neutron spectrum measurement in the channel No. 182/5 of the KFKI WWR-SM reactor
KFKI-1987-27/A S. Krasznovszky et al.	Universal description of inelastic and non(single)-diffractive multiplicity distributions in pp collisions at 250, 360 and 800 GeV/c
KFKI-1987-28/M F. Adorján et al.	VERONA-plus extended core-monitoring system for WWER-440 type nuclear power plants
KFKI-1987-29/G J. Végh et al.	Application of boron filters for neutron spectrum determination purposes in various neutron environments
KFKI-1987-30/E N. Menyhárd	Inhomogeneous mean field approximation for phase transitions in probabilistic cellular automata - An example

KFKI-1987-31/M G. Németh et al.	Computation of generalized Padé approximants
KFKI-1987-32/E I. Pócsik	Lone-pair model for high temperature superconductivity
KFKI-1987-33/B L.B. Szabados	Causal boundary for strongly causal space-time
KFKI-1987-34/A Z. Fodor et al.	Proton detection efficiency of a plastic scintillator telescope
KFKI-1987-35/C R.Z. Sagdeev et al.	Near nuclear region of comet Halley based on the imaging results of the VEGA mission
KFKI-1987-36/E Gy. Szabó	Thermodynamic aspects of chemically curved crystals
KFKI-1987-37/A T. Nagy et al.	Lepton + lepton + photon decays and lepton g-2 factors in gauge theories
KFKI-1987-38/K S. Deme et al.	Real-time computing in environmental monitoring of a nuclear power plant
KFKI-1987-39/K L. Koblinger	A review of Monte Carlo techniques used in various fields of radiation protection
KFKI-1987-40/A J. Balog et al.	Lattice classification of the four-dimensional heterotic strings
KFKI-1987-41/E I. Furó et al.	Evidence of antiferromagnetic ordering in La_2CuO_4 : re-interpretation of ^{139}La nuclear quadrupole resonance (NQR) data
KFKI-1987-42/J Á. Vértes et al.	Kinetic energy distribution of ions generated by laser ionization sources
KFKI-1987-43/E Z. Juhász	Variations of the transfer function during $\text{Bi}_4\text{Ge}_3\text{O}_{12}$ growth
KFKI-1987-44/G A. Gács et al.	Simulation of the dynamic behaviour of the secondary circuit of a WWER-440 type Nuclear Power Plant
KFKI-1987-45/M,N H. Koenig et al.	An intelligent protocol workstation
KFKI-1987-46/M,N P. Ecsedi Tóth et al.	Formal description oriented performance evaluation of protocols
KFKI-1987-47/A N.P. Aleshin et al.	Study of proton-deuteron break-up reaction in exclusive experiment at 1 GeV
KFKI-1987-48/E B. Sas et al.	Scattering mechanisms and transport properties of FeTMB amorphous alloys
KFKI-1987-49/E A.G. Balogh et al.	Positron annihilation study on Y-Ba-Cu-O high T_c superconductors

Kiadja a Központi Fizikai Kutató Intézet
Felelős kiadó: Szegő Károly
Szakmai lektor: Bencze Gyula
Nyelvi lektor: Bakos József
Példányszám: 230 Törzsszám: 87-367
Készült a KFKI sokszorosító üzemében
Felelős vezető: Tőreki Béláné
Budapest, 1987. augusztus hó