



DEVELOPMENT OF VERY-HIGH-DENSITY LOW-ENRICHED-URANIUM FUELS

J. L. Snelgrove, G. L. Hofman, C. L. Trybus, T. C. Wienczek

Argonne National Laboratory
Argonne, Illinois U.S.A.

INTRODUCTION

Fuel development has been a cornerstone of the U.S. Reduced Enrichment for Research and Test Reactors (RERTR) program since its inception in 1978. This development work, performed cooperatively with many partners internationally, resulted by 1987 in the qualification of several dispersion fuels having significantly increased densities: UAl_x-Al at 2.3 g U/cm^3 , U_3O_8-Al at 3.2 g U/cm^3 , and U_3Si_2-Al at 4.8 g U/cm^3 . Approximately 20 reactors have been converted from high-enriched uranium (HEU) to low-enriched uranium (LEU), and several new LEU reactors have been built using these fuels. In most cases the uranium silicide fuel has been used.

Although a fuel with a uranium density of 4.8 g U/cm^3 is sufficient to convert approximately 90% of the research reactors outside the U.S. which used HEU of U.S. origin in 1978, conversion of the remaining reactors, which use a significant quantity of HEU, require fuels having considerably higher densities. Therefore, the RERTR program continued to develop methods to fabricate plates containing higher loadings of uranium silicide fuels until funding constraints forced an end to this work at the end of September 1989. CERCA, one of the RERTR program's key partners in the development of uranium silicide dispersion fuel, continued its development efforts and announced in 1993 that it had developed an advanced fabrication process which allowed the loading of U_3Si_2-Al fuel to be increased to 6.0 g U/cm^3 [1].

Even though development of higher-density fuels was stopped, analysis of the irradiation experiments performed earlier in the RERTR program continued, resulting in a better understanding of the fundamental behavior of these fuels. Also, work continued to better understand and refine dispersion fuel fabrication techniques. Papers reporting these results have been presented annually at the RERTR international meetings. During this period of decreased fuel development activity within the RERTR program, development of uranium silicide dispersion fuel in the U.S. continued under the auspices of Oak Ridge National Laboratory's (ORNL's) Advanced Neutron Source (ANS) project, with Argonne National Laboratory (ANL) designated as the lead fuel development laboratory [2]. A series of three irradiation experiments in the High Flux Isotope Reactor (HFIR) at ORNL provided data on fuel behavior at high temperatures and high fission rates, and revealed that there are limits to the use of U_3Si_2-Al under these conditions. Results from the most recent of these experiments prompted a major new analysis of U_3Si_2-Al fuel irradiation behavior [3]. Irradiation performance modeling was also emphasized since fuels could not be tested at or beyond ANS conditions. The advances made during this interim period have helped provide a good basis for further development of dispersion fuels.

In 1994 the Department of Energy announced its intention to resume the development of very-high-density fuels to address needs of existing and new research and test reactors. However, owing to pressures of a shrinking federal budget, funding for this work could not be made available until last March. This paper describes the plans and schedule of this new development work.

GOAL AND APPROACH

We have set a goal of achieving a uranium density in a dispersion fuel meat of 8 to 9 g U/cm^3 . We think that such a density is achievable from the fabrication point of view, and it matches the

RERTR program's assessments of uranium densities needed to convert the reactors not convertible using 4.8 g U/cm³ U₃Si₂ fuel. Of course, irradiation behavior and fabrication costs will ultimately determine the success of any proposed fuel.

We think that the best chance of successfully developing a fuel with acceptable fabrication cost lies with extension of the current aluminum-based dispersion fuel concept. Since CERCA's experience with highly loaded U₃Si₂-Al [1] and UN-Al [4] fuels indicates that one is not likely to achieve a fuel volume loading greater than 55% in a commercially viable process, fuel dispersants with very-high uranium densities, ≥15 g U/cm³, must be used. With the exception of U₆Fe and U₆Mn, which were tested earlier in the RERTR program and shown to be subject to breakaway swelling at relatively low burnups [5, 6], and the similar compounds U₆Co and U₆Ni, which are also expected to exhibit poor swelling behavior, no uranium compound meets our density requirement.

Therefore, only pure uranium metal or alloys of uranium and small amounts of other metals can be considered as fuel dispersants. Although pure uranium is a notoriously poor performer under irradiation, a series of alloys which maintain uranium in the metastable γ phase have shown good irradiation performance in bulk form under fast reactor conditions. Examples of such alloys are listed in Table 1.

Table 1. Densities of Representative γ-Phase Uranium Alloys

Alloy*	Density, g/cm ³	U Density, g/cm ³
U-9Mo	17.0	15.5
U-5Mo	17.9	17.0
U-3Zr-9Nb	16.2	14.3
U-4Zr-2Nb	17.3	16.3

*Alloying element amount given in wt. %.

Our experience with the U₃Si₂-Al dispersion fuel taught us that the key issues which must be addressed are the reaction of the fuel alloys with the matrix and the irradiation behavior of the fuel alloys and of any reaction products. Should reaction of the fuel alloys with an aluminum matrix be excessive, we will investigate the use of a magnesium matrix while retaining the aluminum cladding, since magnesium does not form compounds with uranium. We have also considered using zirconium as both matrix and cladding material, but we do not currently plan to pursue this option owing to concerns about fabrication cost.

PLANS AND SCHEDULE

Fabrication

During the early stages of the RERTR program, fabrication development was performed at ANL's Illinois site (ANL-East), at Oak Ridge National Laboratory (ORNL), and at the Idaho National Engineering Laboratory (INEL). However, by early 1996 only a very small development group at ANL-East remained. Therefore, a major increase in our fabrication development capacity was required to support an aggressive fuel development effort. In order to utilize best the resources available within ANL, we decided to augment the fabrication development group at ANL-East and to establish a new fabrication development laboratory and group at ANL's Idaho site (ANL-West). The procurement process for most of the equipment needed at ANL-West is underway, and detailed installation plans are being prepared. In addition, we have reached the currently required staffing levels at both sites. At ANL-West we have already begun to produce fuel alloys and expect to begin

producing fuel powder, by mechanical means, and compacts for small test plates by the end of November 1996. We anticipate that the development laboratory will be ready for full use before the end of CY 1997, when the installation of the longest-lead item, the rolling mill, will have been completed. In the meantime, we will carry out all rolling operations at ANL-East. In particular, the first rolling experiments have already been performed and fuel plates for the initial irradiation tests (discussed below) are scheduled to be rolled during the first quarter of CY 1997.

We plan to follow the development pattern that worked so successfully for the uranium silicide fuel, that is, to limit our fabrication development to the study of basic issues and to the production of small fuel plates for irradiation testing and to depend on the commercial fabricators to adapt and extend our results to the fabrication of full-sized fuel plates or tubes. We have held preliminary discussions with both Babcock and Wilcox (B&W) and CERCA. Both are interested in participating but will need to assess further the commercial potential of the proposed fuels before deciding the amounts of company resources which can be committed to the required development work.

ANL and the Korea Atomic Energy Research Institute (KAERI) are setting up a cooperation agreement under which the use of atomized fuels will be explored. KAERI recently completed a study of fuel-matrix reaction rates in dispersions of U-Mo alloys in aluminum, with encouraging results [7]. KAERI has agreed to provide a small quantity of U-Mo powder for fabrication development work at ANL.

Materials Properties Studies

In order to address the key issues stated above, a number of studies are planned on the phase structure of the uranium alloys and diffusion of the matrix materials into the alloys. We expect to make substantial progress in this work over the next year. ANL is also negotiating a cooperation agreement with the A. A. Bochvar All-Russian Research and Development Institute of Inorganic Materials in Moscow, under which phase studies of interacting materials is one area of possible collaboration.

Irradiation Behavior Experiments

Little is known about the irradiation behavior of the proposed fuel alloys when they are dispersed in aluminum or about the behavior of the fuel itself at the high burnups typical of research and test reactors. Our highest priority is to begin irradiation screening tests of the proposed dispersions. We are planning to perform these irradiations in the Advanced Test Reactor (ATR) at INEL and to perform the postirradiation examinations at ANL-West. All of the preparatory activities required for the irradiations are underway, including design of the experiment rig, safety analysis of the experiment, and coordination with the ATR experiment staff.

Because of space limitations in irradiation holes near the core, the fuel plates (which we are calling microplates) must be much smaller than the miniplates irradiated previously by the RERTR program in the Oak Ridge Research Reactor (ORR). The current design calls for microplates with outside dimensions 76 mm x 22 mm x 1.3 mm, compared to the 114 mm x 51 mm x 1.3 mm dimensions of a typical ORR miniplate. The microplates will be produced using 9.5-mm-diameter cylindrical compacts, resulting in an elliptical-shaped fuel zone with nominal dimensions of 57 mm x 9.5 mm x 0.5 mm and an area of $<500 \text{ mm}^2$, whereas the rectangular fuel zone of the typical miniplate measured 102 mm x 46 mm x 0.5 mm and had an area of 4692 mm^2 . Nevertheless, mechanical analyses have shown that the fuel zone area of the microplate is large enough to behave in the same manner as that of a much-larger plate.

Since the first tests will focus on fuel particle-matrix interactions and fuel particle swelling, it is not necessary to test plates with uranium densities approaching the 8 to 9 g U/cm³ goal. In fact, it is much more important to obtain results as quickly as possible. Therefore, in order to minimize heat removal problems in the design of the irradiation rig and to minimize fuel plate fabrication problems, we will limit the uranium density to no more than 4.8 g U/cm³.

The uranium alloy fuels to be tested are listed in Table 2. We know that both the resistance to reaction with aluminum and the γ -phase stability of these alloys increases with increasing amounts of alloying addition; so we designed this test matrix to establish the types and minimum amounts of alloying additions necessary. We also plan to test a U_2Mo -Al dispersion, since U_2Mo may be formed during the irradiation of the U-Mo alloys, and U_3Si_2 -Al, in order to compare the performance of the microplates with that of previously irradiated miniplates and full-sized plates. The current design allows 16 microplates to be irradiated in one module and three modules to be irradiated in one ATR irradiation position. We currently plan to begin the irradiation near the end of April 1997. We will irradiate two sets of plates—one to about 40% burnup and the other to about 80% burnup. The first set will require two 45-day ATR cycles. Assuming that we meet this schedule, postirradiation examinations are expected to start around October 1997.

Table 2. Fuel Alloys Being Prepared for Irradiation Screening Tests
(Alloying element amount given in wt.%)

U-10Mo	U-10Mo-0.05Sn	U-9Nb-3Zr
U-8Mo	U-4Mo-0.1Si	U-2Mo-1Nb-1Zr
U-6Mo	U-5Nb-3Zr	U-2Mo-1Nb-1Zr-1V
U-4Mo	U-6Nb-4Zr	U-6Mo-2Ru

After the screening tests, we will test one or more successful candidate fuels in full-sized plates, irradiated either individually or in full elements. Since the U.S. has no facilities suitable to perform such irradiations, we must look to our international partners for such tests. Very preliminary discussions have been held with representatives of the CEA in France and BATAN in Indonesia. Irradiation of single plates may be feasible in KAERI's HANARO reactor.

Out-of-reactor irradiation tests of U_3Si_2 have provided valuable insight into the changes taking place in the fuel particles in the very early stages of irradiation (see, for example, Ref. 8). These studies have included neutron irradiations at ANL's Intense Pulsed Neutron Source (IPNS) and ion-beam irradiations at ANL's High-Voltage Electron Microscope (HVEM) facility. We plan to continue such work with the new fuels. A recent improvement in the ability to measure aluminum diffusion rates at the HVEM facility was funded by the RERTR program and should prove particularly useful.

Irradiation Behavior Modeling

As mentioned previously, modeling has become a very important part of our development work, since it is impossible to anticipate all conditions under which the fuels we develop might be used. We are currently modifying the DART code [9] to incorporate swelling models for uranium alloy dispersion fuels, based on data available from previous irradiations of bulk fuel. We will use the model as a tool to help us understand the observed irradiation behavior of the new fuels. We will be pursuing improvements to our model, especially in the area of mechanical deformations, under the agreement with the Bochvar Institute in Moscow, mentioned earlier.

OTHER FUELS

The RERTR program maintains an interest in several fuels which do not have sufficiently high uranium densities to qualify as very-high-density fuels, namely, U_3Si_2 , UO_2 , and UN. Current activities are briefly discussed below.

U₃Si₂-Al

Because U₃Si₂-Al fuel is being used in many research and test reactors today and is being chosen as fuel for new reactors being designed, the RERTR program remains committed to provide support for current and potential users of this fuel. Our current emphasis is on obtaining a better understanding of the limits to the applicability of U₃Si₂-Al fuel in certain high-temperature, high-fission rate situations [3]. More data are needed to further define those limits. The French CEA is currently irradiating some 5.8 and 6.0 g U/cm³ plates in SILOE, and we have been discussing a collaboration with the CEA in performing postirradiation examinations of these plates. In addition, we are considering the possibility of performing another irradiation in the HFIR.

The ANL-KAERI cooperation agreement also calls for the irradiation in HANARO of miniplates fabricated in the U.S., some containing atomized U₃Si₂ powder produced by KAERI and some containing the traditional comminuted U₃Si₂ powder in order to demonstrate the acceptable irradiation characteristics of the atomized fuel. A miniplate irradiation rig for HANARO is currently being designed, and preliminary thermal-hydraulic safety calculations for the experiment have been completed.

UO₂

Considerable experience in the behavior of U₃O₈-Al dispersion fuel was obtained during the early phases of the RERTR program. Our interest in UO₂-Al fuel has been kindled by our collaboration with the Russian RERTR program, in which that fuel is being tested up to 3.8 g U/cm³ for use in converting certain Russian-designed research reactors to use LEU. We have revised the DART code to include a model for uranium oxide, based on the U₃O₈ data [10]. We expect to continue to work with our Russian colleagues to evaluate the results of irradiation tests planned to begin within the next year.

UN

In 1994, CERCA reported that uranium densities of about 7.0 g U/cm³ could be achieved in UN-Al dispersion fuel by a commercially acceptable process [4]. Although this achievement represented a significant advance in uranium density, a study performed at ANL [11] has shown that the rather-large thermal neutron absorption cross section of nitrogen substantially reduces the advantage of UN-Al fuel over U₃Si₂-Al fuel at the same fuel volume loading. We understand, however, that concerns about problems presented by uranium silicide fuels in the back end of the fuel cycle have prompted some consideration of the use of UN as a substitute for U₃Si₂. We have found only one reference to irradiation of UN-Al fuel [12]. The swelling of UN-Al fuel at about 14 vol.% loading was found to be greater than that of U₃O₈-Al fuel at a similar volume loading. Irradiation behavior data at high loadings of UN are not available; however, based on the low-loading data and our evaluation of U₃O₈-Al swelling [10], we think that severe burnup limits will be required for high-density UN-Al fuel. Nevertheless, the RERTR program will be happy to collaborate in evaluating the usefulness of this fuel as an alternative to U₃Si₂.

CONCLUSIONS

The RERTR program has recently begun an aggressive effort to develop dispersion fuels for research and test reactors with uranium densities of 8 to 9 g U/cm³, based on the use of γ -stabilized uranium alloys. Fabrication development teams and facilities are being put into place, and preparations for the first irradiation test are in progress. The first screening irradiations are expected to begin in late April 1997 and the first results should be available by the end of 1997. Discussions with potential international partners in fabrication development and irradiation testing have begun.

REFERENCES

1. J. P. Durand and Y. Fanjas, "LEU Fuel Development at CERCA: Status as of October 1993," Proc. 16th International Meeting on Reduced Enrichment for Research and Test Reactors, October 4-7, 1993, Oarai, Japan, JAERI-M 94-02, pp. 71-78, March 1994.
2. G. L. Copeland, "Fuel Qualification Plan for the ANS Reactor," ORNL/M-4324, July 1995.
3. G. L. Hofman, J. Rest, J. L. Snelgrove, T. Wiencek, and S. Koster van Groos, "Aluminum-U₃Si₂ Interdiffusion and Its Implication for the Performance of Highly Loaded Fuel Operating at Higher Temperatures and Fission Rates," paper presented at the 19th International Meeting on Reduced Enrichment for Research and Test Reactors, October 6-10, 1996, Seoul, Korea.
4. J. P. Durand, P. Laudamy, and K. Richter, "Preliminary Developments on MTR Plates with Uranium Nitride," Proc. 1994 International Meeting on Reduced Enrichment for Research and Test Reactors, September 18-23, 1994, Williamsburg, Virginia, ANL/RERTR/TM-20, in press.
5. G. L. Hofman, R. F. Domagala, and G. L. Copeland, "Irradiation Behavior of Low-Enriched U₆Fe-Al Dispersion Fuel Elements," *J. Nucl. Mater.* **150**, 238-243, 1987.
6. G. L. Hofman and L. A. Neimark, "Prospects for Stable High-Density Dispersion Fuels," Proc. X International Meeting on Reduced Enrichment for Research and Test Reactors, Buenos Aires, Argentina, September 28 - October 1, 1987.
7. K. H. Kim, D. B. Lee, C. K. Kim, and I. H. Kuk, "Development of High Loading U-Mo Alloy Fuel by Centrifugal Atomization," paper presented at the 19th International Meeting on Reduced Enrichment for Research and Test Reactors, October 6-10, 1996, Seoul, Korea.
8. R. C. Birtcher, J. W. Richardson, and M. H. Mueller, "Amorphization of U₃Si₂ by Ion or Neutron Irradiation," *J. Nucl. Mater.* **230**, 158-163, 1996.
9. J. Rest, "The DART Dispersion Analysis Tool: A Mechanistic Model for Predicting Fission-Product-Induced Swelling of Aluminum Dispersion Fuels," ANL-95/36, August 1995.
10. G. L. Hofman, J. Rest, and J. L. Snelgrove, "Irradiation Behavior of Uranium Oxide-Aluminum Dispersion Fuel," paper presented at the 19th International Meeting on Reduced Enrichment for Research and Test Reactors, October 6-10, 1996, Seoul, Korea.
11. M. M. Bretscher, J. E. Matos, and J. L. Snelgrove, "Relative Neutronic Performance of Proposed High-Density Dispersion Fuels in Water-Moderated and D₂O-Reflected Research Reactors," paper presented at the 19th International Meeting on Reduced Enrichment for Research and Test Reactors, October 6-10, 1996, Seoul, Korea.
12. M. J. Graber, W. F. Zelezny, and R. A. Moen in *Annual Progress Report on Reactor Fuels and Materials Development for FY 1965*, W. C. Francis, Ed., IDO-17154, p. 11, February 1966.